Ver: A0

NO: 900.869.503.214

PX803035 Battery Spec

Model: <u>PX803035</u>

Customer P/N: 900.869.503.214

Cell Type: <u>PX803035</u>

Nominal Voltage: 3.7V

Capacity: 800mAh

| Draft | Checking | Approved | Customer Confirmation |
|-------|----------|----------|-----------------------|
| Dora | Peter | | |

1. Revision History

| Revision | Date | Editor | Contents |
|----------|------------|--------|----------|
| A0 | 2018-09-10 | Dora | Draft |
| | | | |
| | | | |
| | | | |
| | | | |

Product Specification

Single cell

| No. | Item | General Parameter | | Remark |
|-----|--------------------------------------|--|------------|---|
| | | Typical | 800mAh | Standard discharge (0.2C) after |
| 1 | Rated Capacity | Minimum | 780mAh | Standard charge |
| 2 | Nominal Voltage | 3.7V | 1 | Mean Operation Voltage |
| 3 | Voltage at end of Discharge | 2.75V | | Discharge Cut-off Voltage |
| 4 | Charging Voltage | 4.2±0.03V | | |
| 5 | Internal Impedance | ≤220mΩ | | Internal resistance measured at AC 1KHZ after 50% charge The measure must uses the new batteries that within one week after shipment and cycles less than 5 times |
| 6 | Weight | About 20 g | | |
| 7 | Standard charge | Constant Current 0.2C Constant Voltage 4.2V 0.01 C cut-off | | |
| 8 | Standard discharge | Constant current 0.2C end voltage2.75V | | |
| 9 | Fast charge | Constant Current 1.0C Constant Voltage 4.2V 0.01C cut-off | | |
| 10 | Fast discharge | Constant current 1.0C end voltage 2.75V | | |
| 11 | Maximum Continuous Charge Current | 1.0C | | |
| 12 | Maximum Continuous Discharge Current | 1.0C | | |
| 12 | Operation Temperature | Charge: 0~45°C | | 60±25%R.H. |
| 13 | Range | Discharge: -20~60°C | | Bare Cell |
| 14 | Storage Temperature Range | Less than 1 year: -20~2 | 25°C | 60±25%R.H. |
| 14 | Storage reinperature kange | less than 3 months: -2 | 0~40°C | at the shipment state |
| 4-5 | | Length (L) | 35.0±0.5mm | |
| 15 | Single cell | Width (W) | 30.0±0.5mm | Initial Dimension |
| | | Thickness (T) | 8.0±0.2mm | |

Ver: A0

NO: 900.869.503.214

Pack Battery

| No. | Item | General Parameter | | Remark |
|-----|--------------------------------------|--|----------------------|---|
| 1 | Dated Canacity | Typical | 800mAh | Standard discharge (0.2C) after |
| 1 | Rated Capacity | Minimum | 780mAh | Standard charge |
| 2 | Nominal Voltage | 3.7V | | Mean Operation Voltage |
| 3 | Voltage at end of Discharge | 2.75V | | Discharge Cut-off Voltage |
| 4 | Charging Voltage | 4.2±0.03V | | |
| 5 | Internal Impedance | ≤280mΩ | | Internal resistance measured at AC 1KHZ after 50% charge The measure must uses the new batteries that within one week after shipment and cycles less than 5 times |
| 6 | Weight | About 25 g | | |
| 7 | Standard charge | Constant Current 0.2C Constant Voltage 4.2V 0.01 C cut-off | | |
| 8 | Standard discharge | Constant current 0.2C end voltage2.75V | | |
| 9 | Fast charge | Constant Current 1.0C Constant Voltage 4.2V 0.01C cut-off | | |
| 10 | Fast discharge | Constant current 1.0C end voltage 2.75V | | |
| 11 | Maximum Continuous Charge Current | 1.5A | | BMS |
| 12 | Maximum Continuous Discharge Current | 1.5A | | BMS |
| 13 | Operation Temperature Range | Charge(充电): 0~45℃ Discharge(放电): -20~60℃ | | 60±25%R.H. Bare Cell |
| 14 | Storage Temperature Range | Less than 1 year: -20~25°C (小于一年: -20~25°C) | | 60±25%R.H. at the shipment state |
| 15 | Pack Battery | Length (L) Width (W) | 37.0±1mm 30.5±1mm | |
| | | Thickness (T) | 8.2±0.5mm | |

Ver: A0

NO: 900.869.503.214

2. Performance And Test Conditions

2.1 Standard Test Conditions

Test should be conducted with new batteries within one week after shipment from our factory and the cells shall not be cycled more than five times before the test. Unless otherwise specified, test and measurement shall be done under

temperature of 20±5°C and relative humidity of 45~85%. If it is judged that the test results are not affected by such

conditions, the tests may be conducted at temperature 15~30°C and humidity 25~85%RH.

2.2 Measuring Instrument or Apparatus

2.2.1 Dimension Measuring Instrument

The dimension measurement shall be implemented by instruments with equal or more precision scale of 0.01mm.

2.2.2 Voltmeter

Standard class specified in the national standard or more sensitive class having inner impedance more than $10k\Omega/V$

2.2.3 Ammeter

Standard class specified in the national standard or more sensitive class. Total external resistance including ammeter and wire is less than 0.01Ω .

2.2.4 Impedance Meter

Impedance shall be measured by a sinusoidal alternating current method(1kHz LCR meter).

2.3 Appearance

There shall be no such defect as flaw, crack, rust, leakage, which may adversely affect commercial value of battery.

2.4 Temperature Dependence of discharge capacity

Table 3 (表 3)

| Discharge Temperature | -10°C | 0°C | 23°C | 60°C |
|---------------------------|-------|-----|------|------|
| Discharge Capacity (0.2C) | 50% | 80% | 100% | 95% |

2.5 Cycle Life and Leakage-Proof

Table 4

| No. | Item | Criteria | Test Conditions |
|-----|-------------------|--|---|
| 1 | Cycle Life (0.5C) | Higher than 70% of the Initial Capacities of the Cells | Carry out 500cycle Charging/Discharging in the below condition. ◆ Charge: Standard Charge ◆ Discharge:0.5C to 2.75 V ◆ Rest Time between charge/discharge:30min. ◆ Temperature:20±5°C |
| 2 | Leakage-Proof | No leakage (visual inspection) | After full charge with standard charge, store at 55±3°C, 60±10%RH for 1 week. |

3. Mechanical characteristics and Safety Test for Cell

Table 5 (Mechanical characteristics)

| No. | Items | Test Method and Condition | Criteria |
|----------------------------|-------------------------|--|--|
| | | After standard charging, fixed the cell to vibration table and subjected to vibration cycling that the frequency is to be varied | No leakage |
| 1 | Vibration Test | at the rate of 1Hz per minute between 10Hz an 55Hz, the excursion of the vibration is 1.6mm. The cell shall be vibrated for 30 minutes per axs of XYZ axes. | No fire |
| 2 | Drop Test | The cell is to be dropped from a height of 1 meter twice onto concrete ground. | No explosion, No fire, no leakage. |
| Item | Battery Condition | Test Method | Requirements |
| Crush | Fresh, | Crush between two flat plates. Applied force is about | No explosion, |
| Crusii | Fully charged | 13kN(1.72Mpa) for 30min. | No fire |
| Short Circuit (20°C) | Fresh, Fully charged | Each test sample battery, in turn, is to be short-circuited by connecting the (+) and (-) terminals of the battery with a Cu wire having a maximum resistance load of 0.1Ω . Tests are to be conducted at room temperature ($20\pm2^{\circ}C$). | No explosion, No fire The Temperature of the surface of the Cells are lower than 150°C |
| Short Circuit (60°C) | Fresh, Fully charged | Each test sample battery, in turn, is to be short-circuited by connecting the (+) and (-) terminals of the battery with a Cu wire having a maximum resistance load of 0.1Ω .Tests are to be conducted at temperature($60\pm2^{\circ}C$). | No explosion, No fire The Temperature of the surface of the Cells are lower than 150°C |
| Impact | Fresh, Fully charged | A 56mm diameter bar is inlayed into the bottom of a 10kg weight. And the weight is to be dropped from a height of 1m onto a sample battery and then the bar will be across the center of the sample | No explosion, No fire |



| Forced | Fresh, | Discharge at a current of 1.0Cfor 2.5h. | No explosion, |
|---------------------------|-------------------------|--|--------------------------|
| Discharge | Fully charged | | No fire |
| Nail Pricking (3mm) | Fresh, Fully charged | Prick through the sample battery with a nail having a diameter of 3mm and remain 2h. | No explosion, No fire |

4. Protection circuit

(PCM Standard)

| Item Symbol | | Content | Criterion |
|---------------------------|--------------------|-------------------------------------|------------------------|
| Current | 1 | Max. Charging Current | 1.5A |
| Current | IDP | Max. Discharging | 1.5A |
| | V _{DET1} | Over charge detection voltage | 4.28±0.05V |
| Over charge Protection | tVDET1 | Over charge detection delay time | 80–200ms |
| | V _{REL1} | Over charge release voltage | 4.10±0.05V |
| | V _{DET1} | Over discharge detection voltage | 2.40±0.10V |
| Over discharge protection | tV _{DET1} | Over discharge detection delay time | 40-120ms |
| | V _{REL1} | Over discharge release voltage | 3.00±0.1V |
| | V _{DET3} | Over current detection voltage | 1.30±0.5V |
| Over current | IDP | Over current detection current | 3.5±1.5A |
| protection | tV _{DET3} | Detection delay time | 5-20ms |
| | | Release condition | Cut load |
| | | Detection condition | Exterior short circuit |
| Short protection | Tshor | Detection delay time | 5-120ms |
| | | Release condition | Cut short circuit |
| Interior resistance | Ros | Main loop electrify resistance | VC=2.5V,RDS≤34mΩ |
| Current IDD | | Current consume in normal operation | 3.0µА Туре 6.0µА Мах |

Ver: A0

NO: 900.869.503.214

5. Handling of Cells

- 5.1 Consideration of strength of film package
 - 1) Soft Aluminium foil

Easily damaged by sharp edge parts such as pins and needles, Ni-tabs, comparing with metalcan-cased LIB.

- 2). Sealed edge may be damaged by heat above 100°C, bend or fold sealed edge.
- 5.2 Prohibition short circuit

Never make short circuit cell. It generates very high current which causes heating of the cells and may cause electrolyte leakage, gassing or explosion that are very dangerous.

The Power-Xtra tabs may be easily short-circuited by putting them on conductive surface.

Such outer short circuit may lead to heat generation and damage of the cell.

An appropriate circuitry with PCM shall be employed to protect accidental short circuit of the battery pack.

5.3.Mechanical shock

Power-Xtra cells have less mechanical endurance than metal-can-cased LIB.

Falling, hitting, bending, etc. may cause degradation of Power-Xtra characteristics.

5.4 Handling of tabs

The battery tabs are not so stubborn especially for aluminum tab.

Don't bend tab.

Do not bend tabs unnecessarily.


6. Storing the Batteries

The batteries should be stored at room temperature, charged to about 30% to 50% of capacity. We recommend that batteries be charged about once per half a year to prevent over discharge.

Ver: A0

NO: 900.869.503.214

7. Dimension 尺寸



| | PCM | Normal PCM(1.5A) |
|------------------------|------------------|------------------|
| | Length Cable (L) | 100±5mm |
| | Height (H) | 37.0±1mm |
| Dimensions (Units: mm) | Width (W) | 30.5±1mm |
| (Units: mm) | Thickness (T) | 8.2±0.5mm |
| | Cable 号 | UL1007#26AWG |
| | L1 | 2mm |

8. Drawing of Label 标签图

PET 透明标签。二维码内容为 8680187004903,日期按出货月份更改。YY 为年,MM 为月,年在前,月份在后(年月),如: 1607(2016年07月)。标签格式如下:



Ver: A0

NO: 900.869.503.214

Power-XTRA

PX803035

3.7V 800mAh Lithium Polymer Battery with PCM

• Rechargeable Li-ion / Polymer -

Caution:
Do not short-circuit
Do not disassemble
May explode if disposed of in fire

Made in China / 1807



900.869.503.214

9. Drawing Packing 包装图

整齐装托盘,内置防潮袋,每箱不超 10KG;客户定制 Logo 纸箱,外箱 Logo 格式如下:

Power-XTRA

ENA-13 Bar code 条形码/侧唛:

贴于纸箱正/背两侧,侧唛尺寸 130*100mm (侧唛尺寸视情况而定):

| PO NO. | Order 16-8 | 根据每次订单更改 |
|-----------------|-----------------|-----------------|
| MODEL NO. | 900.869.503.214 | |
| QTY | 500PCS | ₹ □□ 根据每箱数量更改 |
| DATE | YYYY-MM-DD | √──根据出货日期更改 |
| Made in China | | |
| 8 680187 004903 | | |